

(19) World Intellectual Property Organization  
International Bureau(43) International Publication Date  
27 February 2003 (27.02.2003)

PCT

(10) International Publication Number  
WO 03/017333 A1(51) International Patent Classification<sup>7</sup>: H01L 21/00

(21) International Application Number: PCT/US02/11104

(22) International Filing Date: 2 April 2002 (02.04.2002)

(25) Filing Language: English


(26) Publication Language: English

(30) Priority Data:  
PCT/US01/25874 17 August 2001 (17.08.2001) US(71) Applicant (for all designated States except US): MID-  
WEST RESEARCH INSTITUTE [US/US]; 425 Volker  
Boulevard, Kansas City, MO 64110 (US).

(72) Inventors; and

(75) Inventors/Applicants (for US only): LI, Xiaonan  
[US/US]; 1591 Prouty Drive, Evergreen, CO 80439  
(US). YAN, Yanfa [CN/US]; 11888 W. Aqueduct Drive,Littleton, CO 80127 (US). COUTTS, Timothy, J.  
[US/US]; 1229 Pomegranate lane, Golden, CO 80401  
(US). GESSERT, Timothy, A. [US/US]; 29801 Kennedy  
Gulch Road, Conifer, CO 80433 (US). DEHART, Clay,  
M. [US/US]; 4615 west 112th Court, Westminster, CO  
80031 (US).(74) Agents: WHITE, Paul, J. et al.; National Renewable En-  
ergy Laboratory, 1617 Cole Boulevard, Golden, CO 80401  
(US).(81) Designated States (national): AE, AG, AL, AM, AT, AU,  
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,  
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,  
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,  
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,  
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,  
SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,  
VN, YU, ZA, ZM, ZW.(84) Designated States (regional): ARIPO patent (GH, GM,  
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),

[Continued on next page]

(54) Title: METHOD FOR PRODUCING HIGH CARRIER CONCENTRATION P-TYPE TRANSPARENT CONDUCTING OX-  
IDES

(57) Abstract: A method for producing transparent p-type conducting oxide films without co-doping plasma enhancement or high temperature comprising: a) introducing a dialkyl metal at ambient temperature and a saturated pressure in a carrier gas into a low pressure deposition chamber; and b) introducing NO alone or with an oxidizer into the chamber under an environment sufficient to produce a metal-rich condition to enable NO decomposition and atomic nitrogen incorporation into the formed transparent metal conducting oxide.

WO 03/017333 A1